

VersaShield®/II

VersaShield® Coated Natural Cotton

Typical Property Sheet

Flame Resistance / Barrier Properties

- California TB 603: Standard Flame (50 & 70 sec.)*
- California TB 603: Extended Flame (100 & 140 sec.)*

**Approved within construction*

Excellent

Passed

Passed

Basis Weight

9.0 oz/yd2

Thickness

30 mils (0.045 in.)

Frazier Porosity / Breathability

25.0 cfm/ft2

Composite Durability

Excellent

- Elmendorf Tear: Machine Direction
Cross Direction

2,100 grams

1,300 grams

- Tensile Strength: Machine Direction
Cross Direction

120 lbs/3" width

170 lbs/3" width

Resistance to Hydrocarbons

Excellent

Resistance to Industrial Cleaners

Excellent

Resistance to Alkaline/PH Values 7.5-14.0

Excellent

Inherent Properties

Soft, Firm (Moldable), Breathable, Cushiony, Opaque, Anti-Skid

Testing in Progress

Fungal Growth — Designed to be an anti-microbial barrier to inhibit the growth of mold and mildew

Bacterial Growth — Designed to inhibit the growth of the Bacterium

Escherichia Coli (E. Coli)

Allergens — Intended to impede the spreading of dust mites

For more information about VersaShield Fire Barrier and consumer product applications, please contact Elk Technologies at 404.338.0639.

VersaShield®/II

All-Natural Fire Barrier

©2005, Elk Specialty Fabric Technologies, Inc. All rights reserved. All trademarks, ®, are registered trademarks of Elk Premium Building Products, Inc., an ElkCorp company.

ELK 
Specialty Fabric
Technologies
www.elkcorp.com